

Testing the virucidal activity of "NANO4-HYGIENE LIFE"

Examination of test surfaces equipped with a virucidal active coating using a praxis-near carrier test system following the RKI-Richtlinie (1995) as well as ISO 21702:2019 against the **Transmissible Gastroenteritis Virus (TGEV-Coronavirus)** - Test run S2 dated 11./12.03.2020

Short report: screening test S2

by

PD Dr. Olaf Thraenhart and Dr. Christian Jursch

Test period: in March 2020
Principal: NANO4LIFE EUROPE L.P.
Vouliagmenis Ave. 318,
Ag. Dimitrios - 173 43
Athens / Greece

Principal: NANO4LIFE EUROPE L.P.
Vouliagmenis Ave. 318,
Ag. Dimitrios - 173 43
Athens / Greece

Products:

- Test surfaces: *Leneta*[®] foil, with the dimensions of 1,6 cm x 6 cm
- 1. test item: test surfaces coated on one side with NANO4-HYGIENE LIFE (containing the active component[s])
- 2. test item: uncoated test surfaces (or coated w/o the active component[s])

Test parameter:

- Test conditions: T = 25 °C and 90 % r.LF
- Protein load: no additional protein load; the virus material (cell culture supernatant) was spread onto the surface(s) w/o any further manipulation/alteration
- Volume to square ratio: 25 µL/cm²
- Virus suspension covered with foil (LDPE, 50 µm) with the dimensions 1,2 x 5 cm (6 cm²)
- Incubation: 1h, 8h and 24h in a climate chamber KBF 115 (Fa Binder)

Test system:

- Transmissible Gastroenteritis Virus of Swine (TGEV-Coronavirus); strain: Toyama 36 [used in test as the model virus for SARS-CoV]
(Origin: Virusbank of the Friedrich Löffler-Institute, Insel Riems, Germany)
- ST75/2 cells (foetal testis cells of swine)
(Origin: Robert Koch-Institute, Berlin, Germany)

Test procedure:

- The test was performed following a. RKI-Richtlinie (1995) as well as b. ISO 21702:2019
- Test principle: quantitative virucidal carrier test at T = 25 °C and 90 % r.LF (climate chamber)
- the test was performed w/o (additional) protein load

Tab. 1: Product samples tested

No.	Product (s)	Storage conditions ¹
#1	Test item / coated with <u>NANO4-HYGIENE LIFE</u> (containing the virucidal active component(s) / „test sample“)	at RT
#2	Test item / uncoated (or coated w/o the virucidal active component(s) / „control sample“)	at RT

¹ = access limited

Test results:

Observations:

- The test surfaces were largely wettable by the aqueous virus suspension; thus, a more or less uniform liquid film could be produced by using glass spatulas.
- After covering the virus with the LDPE foil, the virus material remained stable as a film over the entire observation period and did not dry out. However, a volume reduction was recorded.

Tab. 2.1: Virus control (Virus titration by limiting dilution)

Sample	VK-1a	VK-1b	VK-2a	VK-2b	VK-3a	VK-3b
	Virus control / 1 h		Virus control / 8 h		Virus control / 24 h	
Titer/Test vol. (lg ID ₅₀)	4,2	4,8	4,05	3,9	2,25	2,85
av. virus titer ± K (95%)¹	5,50 ± 0,37 / 1 mL		4,98 ± 0,35 / 1 mL		3,55 ± 0,37 / 1 mL	

¹ = Calculation of the virus titer and its 95% confidence interval according to EN14476

Tab. 2.2: Virus inactivation (Virus titration by limiting dilution)

Sample	In-1a	In-1b	In-2a	In-2b	In-3a	In-3b
	Inactivation / 1 h		Inactivation / 8 h		Inactivation / 24 h	
Titer/Test vol. (lg ID ₅₀)	3,6	3,45	1,35	1,2	≤ 0,30	≤ 0,30
av. virus titer ± K (95%)¹	4,53 ± 0,22 / mL		2,28 ± 0,29 / mL		≤ 1,30 / mL	
Reduction² (lg ID₅₀ ± K [95%])	0,97 ± 0,43		2,70 ± 0,46		≥ 2,25 ± 0,37	

¹ = Calculation of the virus titer and its 95% confidence interval according to EN14476

² = Virus reduction: lg ID₅₀ of virus input (virus control) minus lg ID₅₀ of sample (at the given time point)

Virus inactivation: (cf. Tab. 2)

- When the virus material is distributed onto a surface a certain virus titer reduction could be observed with almost all viruses. This is driven by time and do also occur without any other influence. This is also true for the test virus used in the present testing. After presentation over 8 h and 24 h on the test surface a titer reduction of 0,5 Log was evident after 8 h and about 2 Log after 24 h (cf. tab. 2.1). It should be noted, however, that this reduction can be judged as very low when compared to 1). the general tenacity of coronaviruses and b). other viruses (even non-enveloped viruses).
- In order to assess the virus inactivating capacity of the coating under test as a single factor an individual virus input control was analysed at each time point tested. With the amount of input virus at a given time point (cf. tab. 2.1) and with the correspondent amount of remaining test virus (cf. tab. 2.2) the virus reduction factor can be determined.
- After the incubation time was due and under the test conditions specified above the virus reduction factor associated with the coating containing the active component amounted to RF = 0,97 ± 0,43 after 1 h, to RF = 2,70 ± 0,46 after 8 h and to RF ≥ 2,25 ± 0,37 after 24 h (cf. Tab. 2.2). It should be noted that after 24 h no residual test virus was detectable.

Conclusions:

- The virus film applied on the test items and covered with the LDPE-foil was stable over the entire observation period. This means that the virus film remained in the liquid state even at the end of the longest exposure time (24 h) and was not dried. Thus, a continuous contact between the virus material and the surface of the test carrier was ensured all over the observation period and a distribution of the virus material in the liquid phase driven by diffusion was given.
- After $t = 1$ h a virus reduction of 0,97 Log was recorded (corresponding to 90 % of inactivation) and after $t = 8$ h the virus reduction amounted to $RF = 2,7$ (corresponding to 99,8 % of inactivation). Due to technical reasons demonstration of the virus reduction was limited to $RF \geq 2,25$ after 24 h.
- The data obtained allow the conclusion that there is a virus reduction that can be attributed to the coating containing the active component(s). With the present testing a good virus inactivating activity of the virucidal coating under test was demonstrated against the TGEV-Coronavirus (as the model virus for the SARS-CoV).
- It should also be mentioned that the conditions of ISO 21702 provide for a higher incubation temperature than that used in S1 (25 vs. 21 ° C).
- The virus reduction obtained with $t = 8$ h suggests that at the incubation time $t = 24$ h a higher virus reduction is evident than could be demonstrated with the endpoint titration method. Here, virus titer determination using the *Large Volume Plating (LVP)* can possibly provide an improved statement.

Luckenwalde, 28th of April 2020



Dr. Ch. Jursch
(GF und Laborleiter Eurovir)